

NFA36-201 E420R steel plate/sheet for Fine-grain structural steels, thermomechanically rolled steels

NFA36-201 E420R steel plate/sheet, EN10113 S420M steel plate/sheet, under NFA standard, we can regard E420R steel plate/sheet for Fine-grain structural steels, thermomechanically rolled steel.

NFA36-201 E420R is a technical delivery conditions for thermomechanical rolled weldable fine grain structural steels. S means the structural steel, M means the delivery condition. Capital letter L for the quality with specified minimum values of values of impact energy. The NFA36-201 E420R steel is equivalent to SEW TStE420TM, EN S420M and ASTM A572Gr60 steel grade.

E420R NFA 36-201 Number:1.8825	Comparision of steel grades	
	SEW 083	TStE 420 TM
	EN 10113-3	S420M
	UNI 7382	-
	BS 4360	-
	ASTM	A 572 Gr.60

Chemical Composition of E420R steel

Grade	C max	Si max	Mn max	P max	S max	N max	AL max	Nb max	V max	Ti max	Cr max	Ni max	Mo max	Cu max	CE V max
E420R	0.16 %	0.50 %	1.70 %	0.03 %	0.02 5%	0.02 5%	0.02 %	0.05 %	0.12 %	0.05 %	0.30 %	0.80 %	0.20 %	0.55 %	0.47 %

Mechanical Properties of E420R steel

Temperature	-10	0	20
Notch impact test. Min. absorbed energy	43	47	55

Nominal thickness(mm)	to 16	16-40	40-63	63-80	80-100	100-120
ReH-Minimun yield strength(Mpa)	420	400	390	380	370	365

Nominal thickness(mm)	to 40	40-63	63-80	80-100	100-120
Rm-Tensile strength(Mpa)	520-680	500-660	480-640	470-630	460-620
Nominal thickness(mm)	-				
A-Minimum elongation Lo=5,65√So(%)	19				

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:http://www.shipbuilding-steel.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.