

DIN-SEW083 TStE355TM steel plate/sheet for Fine-grain structural steels, thermomechanically rolled steels

DIN-SEW083 TStE355TM steel plate/sheet, DIN-SEW083 TStE355TM steel plate/sheet, under DIN standard, we can regard TStE355TM steel plate/sheet for Fine-grain structural steels, thermomechanically rolled steel.

DIN-SEW083 TStE355TM is a technical delivery conditions for thermomechanical rolled weldable fine grain structural steels. S means the structural steel, M means the delivery condition. Capital letter L for the quality with specified minimum values of values of impact energy at temperature not lower than -50 degree. It is equal to EN S355ML, NFA36-201 E355FP and ASTM A633Gr.C steel grade.

TStE355TM DIN-SEW 083 Number: 1.8834	Comparison of steel grades	
	EN10113-3	S355ML
	NFA 36-201	E 355 FP
	UNI 7382	Fe E 355 KTTM
	BS 4360	50 EE
	ASTM	A 633 Gr.C

Chemical Composition of EN TStE355TM steel

Grade	C	Si	Mn	P	S	N	AL	Nb	V	Ti	Cr	Ni	Mo	Cu	CE
	max	max	max	max	max	max	max	max	max	max	max	max	max	max	Vmax
TStE 355 TM	0.14%	0.5%	1.6%	0.025%	0.025%	0.02%	0.02%	0.05%	0.1%	0.05%	0.3%	0.5%	0.1%	0.5%	0.45%

Mechanical Properties of EN TStE355TM steel

Temperature	-50	-40	-30	-20	-10	0	20
Notch impact test. Min. absorbed energy	27	31	40	47	51	55	63

Nominal thickness(mm)	to 16	16-40	40-63	63-80	80-100	100-120
ReH-Minimum yield strength(Mpa)	355	345	335	325	325	320

Bebon steel — The most professional exporter on shipbuilding steel

Tel: 0086-371-86151527

 E-mail: bb@bebonchina.com

Fax: 0086-371-86011881

 MSN: bebonchina@hotmail.com

Skype: bebonchina

 Web: <http://www.shipbuilding-steel.com>

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.



BEBON

BebonChina.com

Henan BEBON international co.,ltd

Nominal thickness(mm)	to 40	40-63	63-80	80-100	100-120
Rm-Tensile strength(Mpa)	470-630	450-610	440-600	440-600	430-590
Nominal thickness(mm)	-				
A-Minimum elongation Lo=5,65√So(%)	22				

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:http://www.shipbuilding-steel.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.